

## Classifications

**EN ISO 14343-A**

G 19 12 3 L Si

**AWS A5.9 / SFA-5.9**

ER316LSi

## Characteristics and typical fields of application

Solid wire G 19 12 3 L Si / ER316LSi for joining and surfacing of matching and similar austenitic steels and cast steel grades. Good corrosion resistance. Max. service temperature 400°C.

## Base materials

1.4401 X5CrNiMo17-12-2, 1.4404 X2CrNiMo17-12-2, 1.4409 GX2CrNiMo19-11-2, 1.4429 X2CrNiMoN17-12-3, 1.4432 X2CrNiMo17-12-3, 1.4435 X2CrNiMo18-14-3, 1.4436 X3CrNiMo17-12-3, 1.4571 X6CrNiMoTi17-12-2, 1.4580 X6CrNiMoNb17-12-2, 1.4583 X10CrNiMoNb18-12  
UNS S31600, S31603, S31635, S31640, S31653  
AISI 316L, 316Ti, 316Cb

## Typical analysis

|       | C    | Si  | Mn  | Cr   | Ni   | Mo  |
|-------|------|-----|-----|------|------|-----|
| wt.-% | 0.02 | 0.8 | 1.7 | 18.4 | 12.4 | 2.8 |

## Mechanical properties of all-weld metal - typical values (min. values)

| Condition | Yield strength R <sub>p0,2</sub> | Tensile strength R <sub>m</sub> | Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) | Impact energy ISO-V KV J |
|-----------|----------------------------------|---------------------------------|---|--------------------------|
|           | MPa                              | MPa                             | %   | 20°C                     |
| u         | 430 ( $\geq$ 320)                | 580 ( $\geq$ 510)               | 38 ( $\geq$ 25)                                 | -196°C                   |

u untreated, as-welded – shielding gas Ar + 2.5% CO<sub>2</sub>

## Operating data

| Polarity                        | DC +     | Dimension mm |
|---------------------------------|----------|--------------|
| Shielding gas<br>(EN ISO 14175) | M12, M13 | 0.8          |
|                                 |          | 1.0          |
|                                 |          | 1.2          |
|                                 |          | 1.6          |

## Approvals

TÜV (19798), DB (43.132.93), CE